### **Product Name: Polyether LD8006**

# **Product Introduction**

LD8006 is a high-functionality, high molecular weight polyether suitable for the preparation of high-resilience foam. It effectively improves foam resilience and support, enhancing the plump feeling.

# **Specifications**

#### **Premium Grade**

Product	LD8006	Test Standard
Appearance	Transparent liquid, free of suspended matter	Q/ZHDDZB 05.10.001-2024
Viscosity (25°C), mPa·s	1400 ~ 1900	Q/ZHDDZB 05.10.001-2024
Hydroxyl value, mgKOH/g	26.50 ~ 29.50	Q/ZHDDZB 05.10.001-2024
Water content, %	≤0.050	Q/ZHDDZB 05.10.001-2024
pH value	5.0 ~ 8.0	Q/ZHDDZB 05.10.001-2024
Potassium, mg/kg	≤5	Q/ZHDDZB 05.10.001-2024
Color, APHA	≤100	Q/ZHDDZB 05.10.001-2024

#### **Qualified Grade**

Product	LD8006	Test Standard
Appearance	Transparent liquid, free of suspended matter	Q/ZHDDZB 05.10.001-2024
Viscosity (25°C), mPa⋅s	1500 ~ 2000	Q/ZHDDZB 05.10.001-2024
Hydroxyl value, mgKOH/g	26.00 ~ 30.00	Q/ZHDDZB 05.10.001-2024
Water content, %	≤0.060	Q/ZHDDZB 05.10.001-2024
pH value	5.0 ~ 8.0	Q/ZHDDZB 05.10.001-2024
Potassium, mg/kg	≤8	Q/ZHDDZB 05.10.001-2024
Color, APHA	≤120	Q/ZHDDZB 05.10.001-2024

# **Packaging**

Packaged in clean, dry, sealed, leak-proof dedicated painted iron drums, with a net weight of 200kg per drum; or in tank trucks, flexitanks, or IBCs. Can also be packaged according to customer requirements. Packaging containers must be tightly closed.

# **Storage & Transportation**

During transportation, protect LD8006 strictly from rain and contamination. Handle with care, avoid collision with hard

objects to prevent leakage and damage.

During storage, LD8006 should be stored at room temperature in a ventilated, dry warehouse. Avoid damp environments. Storage temperature should be maintained below 50°C. Avoid direct sunlight. Keep away from water sources and heat sources. Alternatively, store sealed in containers made of steel, aluminum, polyethylene, or polypropylene. To prevent moisture absorption and oxidation, it is recommended to purge containers with nitrogen. Storage temperatures above 60°C may cause product quality degradation. Short-term temperature increases or decreases have minimal impact on product quality, but note that significantly lower temperatures will cause a noticeable increase in viscosity, which may pose difficulties during processing.

#### **Shelf Life**

Under correct storage conditions, the shelf life is one year from the date of production. The product may still be used after this period if re-inspection confirms it meets specifications.

### **Safety Information**

LD8006 is classified as a non-hazardous substance. It has a high flash point and is combustible. In case of fire, use foam, dry powder, steam, or water to extinguish. It is not explosive. It is practically non-toxic, and no special ventilation requirements are needed. The toxicity of general neutral polyether polyols if ingested orally or through contact with skin, eyes, or mucous membranes is negligible. In case of skin contact, wash with soapy water. In case of eye contact, flush with low-pressure clean water or seek medical treatment. Workers can wear eye protection or safety glasses. Eye wash and shower equipment should be available near the work area. The product is generally considered non-hazardous to skin. When working in areas where contact with the product is possible, observe personal hygiene practices. Wash skin that has been in contact with the product using cleaning products before eating, smoking, or leaving the work area.

## **Spill Handling**

Stop the leak if it is safe to do so. For minor spills, absorb with sand or other absorbent material and place into a clean, dry container for subsequent disposal. For large spills, contain the spilled material for recovery and subsequent disposal. Prevent material from entering groundwater or surface water, as it is not readily biodegradable. All collected spill material should be disposed of in accordance with local environmental regulations.

## **Disclaimer**

The information and technical advice provided above are obtained from sources we believe to be reliable. However, we make no warranty, express or implied, regarding the data provided, and offer no guarantees herein. We recommend conducting a series of tests if you intend to use our product. We are not responsible for the application, use, processing, or production of goods based on the technical information we provide, and such responsibilities lie solely with the user. The conditions and methods of handling, storage, use, or disposal of this product are beyond our control and may be beyond our knowledge. In no event shall we be liable for any loss, damage, or expenses incurred due to improper handling, storage, use, or disposal of this chemical.

For more information, please refer to the Technical Safety Data Sheet (SDS) for our product or contact our Market Services department.

# **Contact Information**

Sinochem Dongda (Zibo) Co., Ltd.

Address: Huantai Maqiao Chemical Industry Park, Zibo City, Shandong Province, China

Tel: 0086-0533-7878333

E-mail: dongda@sinochem.com

Website: http://www.lxdd.chemchina.com/

Postal Code: 256405