

Product Technical Data Sheet (TDS)

Polyether BP-2760D - Castor Oil-based Biopolyol

Product Introduction

BP-2760D is a biomass polyether polyol produced using castor oil as the initiator and bimetallic catalysts. This product contains 60wt% castor oil, with a functionality of 2.7 and a molecular weight of 1500-1600. It can be used in polyurethane soft foam, automotive interior products, automotive seats, and high-resilience foam fields. It can also be used in soft adhesive and elastomer formulation systems, especially for producing wear-resistant coatings, flexible adhesives, soft sealants, and elastomers. It has high practical value in industries such as electronic packaging, lipophilicity, high-temperature cooking laminating adhesives, and applications requiring high water resistance.

Product Specifications

Item	BP-2760D	Test Standard
Appearance	Light yellow transparent liquid	Q/ZHDDZB05.10.001-2024
Viscosity (25°C), mPa·s	580~720	Q/ZHDDZB05.10.001-2024
Water Content, %	≤0.050	Q/ZHDDZB05.10.001-2024
pH	5.5~7.5	Q/ZHDDZB05.10.001-2024
Acid Value, mgKOH/g	≤0.080	Q/ZHDDZB05.10.001-2024
Hydroxyl Value, mgKOH/g	95.0~101.0	Q/ZHDDZB05.10.001-2024

Packaging

Packaged in clean, dry, sealed, leak-proof special painted iron drums, net weight 200kg per drum; or in tank trucks, flexitanks, IBCs. Can also be packaged according to customer requirements. Packaging containers must be tightly closed.

Storage & Transportation

During transportation of BP-2760D, protect against rain and contamination. Handle with care, avoid collision with hard objects to prevent leakage.

BP-2760D should be stored in a ventilated, dry warehouse at room temperature. Avoid damp environments. Storage temperature should be kept below 50°C. Avoid direct sunlight. Keep away from water sources and heat sources. Alternatively, store sealed in containers made of steel, aluminum, polyethylene, or polypropylene. To prevent moisture absorption and oxidation, it is recommended to fill the container with nitrogen gas. Storage temperatures above 60°C will lead to product quality degradation.

Short-term temperature increases or decreases have little effect on product quality, but note that viscosity increases significantly at lower temperatures, which may cause some difficulties in production and processing.

Shelf Life

Under correct storage conditions, the shelf life is 1 year from the date of production.

Note: For low-odor products, customers are advised to use them as soon as possible.

Safety Information

BP-2760D is classified as a non-hazardous substance. It has a high flash point and is combustible. In case of fire, use foam, dry powder, steam, or water to extinguish. It is not explosive. It is almost non-toxic and requires no special ventilation. The toxicity of generally neutral polyether polyols upon ingestion or contact with skin, eyes, or mucous membranes is considered negligible. In case of skin contamination, wash with soapy water. In case of eye contact, flush with low-pressure clean water or seek medical treatment. Workers can wear protective goggles or safety glasses to protect their eyes. Eye wash and shower equipment should be available near the workplace. The product is generally considered non-hazardous to skin. When working in areas where contact with the product is possible, pay attention to personal hygiene. Before eating, smoking, or leaving the work area, clean skin that has been in contact with the product using cleaning products.

Spill Handling

Stop the leak if it is safe to do so. For minor spills, absorb with sand or other absorbent material and place in a clean, dry container for subsequent disposal. For large spills, contain the spilled material for subsequent recovery. Prevent material from entering groundwater or surface water, as it is not readily biodegradable. All collected spill material should be disposed of according to local environmental regulations.

Disclaimer

The information and technical advice provided above are obtained from reliable sources. However, we make no express or implied warranties regarding the provided data and offer no guarantees herein. We recommend conducting a series of tests if you intend to use our product. The application, use, processing, or production of products based on the technical information we provide is beyond our control, and therefore the responsibility lies with the user. The conditions and methods for handling, storage, use, or disposal of this product are beyond our control and may exceed our knowledge. In no event shall we be liable for any losses, damages, or expenses incurred due to improper handling, storage, use, or disposal of this chemical.

For more information, please refer to the Technical Safety Data Sheet (SDS) of our product or contact our Market Service Department.

Contact Information

Sinochem Dongda (Zibo) Co., Ltd.

Address: No. 25888, North Outer Ring Road, Huantai County, Shandong Province, China

Tel: 0086-0533-7878333

E-mail: dongda@sinochem.com

Website: <http://www.lxdd.chemchina.com/>

Postal Code: 256405

[Download as PDF](#)

© 2024 Sinochem Dongda (Zibo) Co., Ltd. All rights reserved.